



CHARACTERISTICS	STANDARDS	RESULT	CLASSIFIED
VALENTINA COLLECTION			
Total thickness		9.5mm	
Underlayment thickness		2mm IXPE	
Wear layer		0.75mm (30mil)	
Box Size		18.7 SF/Box	
Planks Per Box		5	
Box Per Pallet		40 or 50 Boxes	
SF per Pallet		748 SF or 935 SF	
Net Weight Per Pallet		2,486 lbs or 3,086 lbs	
Plank Length		1524mm (60")	
Plank Width		228mm (9")	
Finish		EIR (Embossed in Register)	
Construction		Rigid Core SPC	
Surface		V-groove Painted Bevel	
Locking System		Valinge 2G	
Installation Method		Click	
Installation Level		All Grades	
Matching Moldings Available		Available	
Peel Resistance	ISO 24345:2012	Pass	
Thermal Conductivity	ASTM C518-21	0.102 W/(m-K)	
Residual Indentation after Static Load	ASTM F3261-20	0.075mm	
Critical Heat Flux	EN 13501-1:2018	≥11 kW/m2	Bfl-s1
Reaction to Fire Classification	EN 13501-1:2018		Bfl-s1
Wear Resistance	EN 660-2:1999/A1:2003	Fv=1.8mm3/100r	Class T
Dimentional Stability and Curling after Exposure to Heat	ISO 23999:2021	Dimentional stability Curling	MD: 0.10% ; AMD: 0.10% 0mm
Scratch Resistance	ISO 1518-1:2023	Pass	
Staining and Resistance to Chemicals	ISO 26987:2012	Index 0 (Not affected)	
Sliding Behaviour	EN 13893:2002-11	μ = 0,51	DS
Thermal Resistance	ASTM C518-21	0.059 (m2-K)/W	
Formaldehyde	ASTM D6007-2014	not detected	
Film Hardness	ISO 15184:2020	H	
Residual Indentation	ASTM F3261-20	Pass	
Acoustic Sound Insulation	ASTM E492-2009 (R2016) and ASTM E2179-2003 (R2016)	STC: 53-68	
Resistance to Staining	EN 16094-2021 (E)	2.1%	MSR-A1
Castor Chair Test	ISO 4918:2016/AMD 1:2018	Pass	

